

19



Europäisches Patentamt
European Patent Office
Office européen des brevets



11 Publication number:

0 423 780 A2

12

EUROPEAN PATENT APPLICATION

21 Application number: **90119969.5**

51 Int. Cl.⁵: **B22C 1/22**

22 Date of filing: **18.10.90**

30 Priority: **20.10.89 DE 3934940**

43 Date of publication of application:
24.04.91 Bulletin 91/17

64 Designated Contracting States:
CH DE FR GB IT LI NL SE

71 Applicant: **GVT- GIESSEREI
VERFAHRENS-TECHNIK GmbH
Flurstrasse 88
W-8501 Schwarzenbruck(DE)**

72 Inventor: **Cobett, Tom
8861 Grandville Circle
Westminster CA 92683(US)
Inventor: Markham, Neil
4917 Arbor Road
Long Beach CA 90808(US)
Inventor: Teltschik, Ralf
Gsteinacher Strasse 12
W-8501 Schwarzenbruck(DE)**

74 Representative: **Patentanwälte Czowalla .
Matschkur & Partner
Dr.-Kurt-Schumacher-Strasse 23 Postfach
9109
W-8500 Nürnberg 11(DE)**

54 **Novel heat curable organic resin foundry sand binder process.**

57 **A heat curable organic foundry sand binder based upon liquid epoxide or epoxide novolac resin and a latent dicyandiamide or imidazole curing agent, with or without an imidazole accelerator, which may be used as a direct replacement for other "Hot Box" and "Warm Box foundry resin binders.**

EP 0 423 780 A2

NOVEL HEAT CURABLE ORGANIC RESIN FOUNDRY SAND BINDER PROCESS

The invention relates to epoxide or epoxide novolac resins mixed with a latent curing agent, with or without an accelerator, cured by heat for the production of foundry sand molds and cores. It is common practice to refer to these heat curable resin binders as "Hot Box" or "Warm Box" binders since the core box or pattern must be heated to affect curing of the sand, resin, curing agent and accelerator mixture.

5 The "Hot Box" and "Warm Box" processes utilize sand coated with a thermosetting resin in liquid form and a latent curing agent in liquid or dry powder form. This mixing of sand, resin and curing agent is done at ambient temperature. A metal pattern or core box is then heated to a temperature of 200 to 300 degrees C. and the damp mixture of sand, thermosetting resin binder and latent curing agent is applied to it by dropping or by fluidization with air. After a period of a few seconds to several minutes, the pattern or box is
10 inverted or opened. The sand, resin and curing agent mix has now sufficiently hardened so that the mold or core can be handled and stored for later use in the metal casting process. The "Warm Box" process operates at somewhat lower temperatures than the "Hot Box" process.

This type of process is widely used in the foundry industry to make metal castings of high dimensional tolerance. A disadvantage of the "Hot Box" or "Warm Box" process is that the preferred resins are
15 Phenol/Formaldehyde, Urea/Formaldehyde or Furfuryl Alcohol/Formaldehyde or combinations thereof. Formaldehyde is considered to be a toxic material by nearly all industrial nations. There is also a pungent odor generated during the making of the core or mold as well as during metal pouring and shakeout. The problem of toxic materials and/or obnoxious odor exists with most current "Hot Box" and "Warm Box" processes.

20 It is desirable to have a resin binder system that can be used in a similar manner to the "Hot Box" or "Warm Box" processes without exhibiting obnoxious odors or containing toxic materials such as formaldehyde. It is further desirable that the said new resin binder process have the same physical strengths and performance benefits as the existing "Hot Box" and "Warm Box" resin binders, thereby allowing for the utilization of the new resin process with existing equipment and tooling.

25 Epoxide and epoxide novolac resins cured by dicyandiamide with or without an imidazole are used in the aerospace, automotive, electronic, coating and adhesive industries. The cured epoxies are inert, non-toxic polymers. They are not chemically reactive and remain as very stable compounds. There is no presence of formaldehyde or other toxic materials.

It has now been found that a heat curable sand, resin and curing agent mix can be produced utilizing an
30 epoxide or epoxide novolac resin and a latent curing agent with or without an accelerator.

According to the present invention, there is provided a sand, resin, curing agent and accelerator composition comprising a medium to high molecular weight epoxide resin, an epoxide novolac resin, or, a mixture of the two, both having an epoxide equivalent weight of 150 to 250; a latent heat curable curing agent such as dicyandiamide or an imidazole; and possibly an imidazole accelerator. Certain imidazoles will
35 affect the curing of epoxides without the presence of dicyandiamide. These mixtures will quickly harden when exposed to heat.

Accordingly, to produce a flowable sand, resin, curing agent and accelerator mix, it may be necessary to dilute or dissolve the resin, curing agent or accelerator in a solvent such as propylene carbonate, methylglycol, methoxypropanol, methyl lactate or butyl lactate. The resin/diluent solution is applied to the
40 sand at 0.5 to 5.0 percent by weight of the sand. The heat curable latent curing agent and accelerator may be applied to the sand in liquid (with diluent) or powder form at 2.0 to 25.0 percent by weight of the resin. The resulting damp sand mixture is now ready for use by heating it to temperatures in excess of the curing agent and accelerator activation temperature.

In all cases, various accelerators can be used such as modified or unmodified imidazoles, including, but
45 not limited to 2-methyl imidazole, 2-phenyl imidazole and 1-H-imidazole.

The following examples will serve to illustrate the invention.

EXAMPLE A

50

A sand mixture was prepared having the following composition by weight:

98.2 %	Silica Sand AFS Grain Fineness Number 90
1.5 %	Liquid Resin - 80 % Dow DER 331 Epoxide Resin 20 % Propylene Carbonate Diluent
0.3 %	Powder Curing Agent - 100 % Dicyandiamide

5

10 The sand mixture was blown into an AFS Standard Tensile Strength Specimen Core Box which had been heated to 150 degrees C. The test core required 2 minutes of curing time after which it had sufficient strength to be removed from the core box. No odor or smoke were present during the curing cycle. The 24 hour tensile strength of the cured sand core was measured as being over 350 pounds per square inch (over 25 Newtons per square centimeter). The mixed sand was stable for over 1 week at room temperature with

15 no loss of performance.

EXAMPLE B

20 A sand mixture was prepared having the following composition by weight:

98.2 %	Silica Sand AFS Grain Fineness Number 90
1.5 %	Liquid Resin - 40 % Dow DER 331 Epoxide Resin 40 % Dow DER 431 Epoxide Novolac Resin 20 % Propylene Carbonate Diluent
0.3 %	Powder Curing Agent - 100 % Dicyandiamide

25

30

The sand mixture was blown into an AFS Standard Tensile Strength Specimen Core Box which has been heated to 150 degrees C. The test core required 1 minute of curing time after which it had sufficient strength to be removed from the core box. No odor or smoke were present during the curing cycle. The 24 hour tensile strength of the cured sand was measured as being over 350 pounds per square inch (over 25 Newtons per square centimeter). The mixed sand was stable for over 1 week at room temperature with no

35 loss of performance.

40 EXAMPLE C

A sand mixture was prepared having the following composition by weight:

98.3 %	Silica Sand AFS Grain Fineness Number 90
1.5 %	Liquid Resin - 40 % Dow DER 331 Epoxide Resin 40 % Dow DER 431 Epoxide Novolac Resin 20 % Propylene Carbonate Diluent
0.3 %	Powder Curing Agent - 80 % Dicyandiamide 20 % 2-Methyl Imidazole

45

50

55 The sand mixture was blown into an AFS Standard Tensile Strength Specimen Core Box which had been heated to 150 degrees C. The test core required only 30 seconds of curing time after which it had sufficient strength to be removed from the core box. No odor or smoke were present during the curing cycle. The 24 hour tensile strength of the cured sand was measured as being over 350 pounds per square

inch (over 25 Newtons per square centimeter). The mixed sand was stable for over 8 hours at room temperature with no loss of performance.

5 EXAMPLE D

A sand mixture was prepared having the following composition by weight:

10	98.475 %	Silica Sand AFS Grain Fineness Number 90
	1.5 %	Liquid Resin -
		40 % Dow DER 331 Epoxide Resin
		40 % Dow DER 431 Epoxide Novolac Resin
		20 % Propylene Carbonate Diluent
15	0.075 %	1-H-Imidazole

The sand mixture was blown into an AFS Standard Tensile Strength Specimen Core Box which had been heated to 150 degrees C. The test core required only 15 seconds of curing time after which it had sufficient strength to be removed from the core box. No odor or smoke were present during the curing cycle. The 24 hour tensile strength of the cured sand was measured as being over 350 pounds per square inch (over 25 Newtons per square centimeter). The mixed sand was stable for over 8 hours at room temperature with no loss of performance.

25

Claims

1. A sand mixture composition consisting of 0.5 to 5.0 % by weight of an epoxide resin having an epoxide equivalent weight of about 150 to 500, particularly to 250; 0.01 to 1.0 % by weight of a latent heat curable curing agent; and the balance being a clean dry foundry sand.
2. A sand mixture composition according to Claim 1 wherein the epoxide resin may be an epoxide novolac resin or a blend of epoxide resin and epoxide novolac resin.
3. A sand mixture composition according to Claim 2 wherein the epoxide resin and/or epoxide novolac resin may be diluted with a solvent such as propylene carbonate.
- 35 4. A sand mixture composition according to Claim 3 wherein the latent heat curable curing agent is Dicyandiamide.
5. A sand mixture composition according to Claim 4 wherein the latent heat curable curing agent may be accelerated by an Imidazole such as 2-Methyl Imidazole, 2-Phenyl Imidazole or 1-H-Imidazole.
- 40 6. A sand mixture composition according to claim 3 wherein the latent heat curable curing agent is an Imidazole such as 1-H-Imidazole.
7. A method of making bonded sand foundry cores or molds utilizing the sand mixture compositions according to Claims 1 through 6.

45

50

55

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 423 780 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **90119969.5**

(51) Int. Cl.⁵: **B22C 1/22, C08G 59/40**

(22) Date of filing: **18.10.90**

(30) Priority: **20.10.89 DE 3934940**

(43) Date of publication of application:
24.04.91 Bulletin 91/17

(84) Designated Contracting States:
CH DE FR GB IT LI NL SE

(88) Date of deferred publication of the search report:
28.10.92 Bulletin 92/44

(71) Applicant: **GVT- GIESSEREI
VERFAHRENS-TECHNIK GmbH
Flurstrasse 88
W-8501 Schwarzenbruck(DE)**

(72) Inventor: **Cobett, Tom
8861 Grandville Circle
Westminster CA 92683(US)
Inventor: Markham, Neil
4917 Arbor Road
Long Beach CA 90808(US)
Inventor: Teltschik, Ralf
Gstelnacher Strasse 12
W-8501 Schwarzenbruck(DE)**

(74) Representative: **Patentanwälte Czowalla .
Matschkur & Partner
Dr.-Kurt-Schumacher-Strasse 23 Postfach
9109
W-8500 Nürnberg 11(DE)**

(54) **Novel heat curable organic resin foundry sand binder process.**

(57) **A heat curable organic foundry sand binder based upon liquid epoxide or epoxide novolac resin and a latent dicyandiamide or imidazole curing agent, with or without an imidazole accelerator, which may be used as a direct replacement for other "Hot Box" and "Warm Box foundry resin binders.**

EP 0 423 780 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 90 11 9969

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	US-A-3 305 527 (PRICE) 21 February 1967 * the whole document *	1-7	B22C1/22 C08G59/40
X	WPIL DATABASE, Derwent Publications Ltd., London GB AN-85-137709 [23] DW-8523 & JP-60/72636 (NISSAN MOTOR KK) 24 April 1985 * abstract *	1,2	
A	---	4-7	
A	US-A-3 705 872 (WITTENWYLER) 12 December 1972 * column 1, line 14 - line 21 * * column 6, line 36 - column 7, line 69 * * column 8, line 35 - column 9, line 14 *	1-3,7	
A	DE-A-3 433 851 (GURIT-ESSEX) 27 March 1986 * claims 1,2 * * page 14, line 9 - line 28 *	1	
A	KROSCWITZ ET AL 'Encyclopedia of Polymer Science and Engineering, Volume 6' 1986, WILEY-INTERSCIENCE, NEW YORK, USA * entry: "Epoxy Resins"; title: "Aromatic Glycidyl Ether Resins", pages 332-334; tables 2, 3 *	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			B22C C08G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 28 AUGUST 1992	Examiner RIBA VILANOVA M.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	